



Tech Data

AC-9041 Euro-Gloss Clear

AC-9041 Euro Clear is an easy to spray; water white low VOC high quality clearcoat designed for panel repairs and complete refinishing over most aftermarket acrylic enamel, acrylic and urethane basecoat systems. AC-9041 can also be integrated into most acrylic enamel and urethane single stage systems for improved gloss and durability. AC-9041 dries fast and retains high gloss and DOI. AC-9041 provides excellent durability and is resistant to environmental conditions such as sunlight and acid rain. AC-9041 can be buffed to match the original finish after 8-12 hours air dry and can be buffed for several days. When mixed 2/1 with AH-6370, AH-6380 or AH-6390 series hardeners, the AC-9041 Clear has a sprayable VOC of just 4.2 lbs/gal making it one of the lowest VOC painter friendly clearcoats in the industry.

Products

AC-9041
AH-6370
AH-6380
AH-6390

Euro Gloss Clear
Urethane Catalyst Fast
Urethane Catalyst Medium
Urethane Catalyst Slow

Application

Surface Preparation, Bare Substrates

Solvent wash surface with a good grade wax and grease remover such as AS-2900 and wipe dry with a clean cloth. Apply three single wet coats of AP-8300 Series Epoxy Primer according to instructions on data sheet. Follow with two to three coats of AP-8030 Super-Fill Primer D.T.M.

Surface Preparation, Prepainted Substrates

Wash surfaces with a mild detergent and hot water. Rinse with clean water and wipe dry with a clean cloth. Solvent clean with AS-2900 Clean Ease. Wipe dry with a clean cloth. Sand original paint and repair damaged areas with a good quality non-staining body filler. Apply 2-3 wet coats AP-8030 Super-Fill Primer D.T.M. as needed to fill voids and block sand with 180 to 280 grit treated sandpaper. Finish sand repaired area with 320 grit sandpaper using a DA Sander. For spot repairs, scuff sand area where basecoat and clearcoat will be blended with 320 to 600 grit sandpaper or nylon scuff pad. For overall refinishing, scuff sand the entire car with 320 grit sandpaper or fine scuff pad.

Sealer

Apply appropriate sealers such as AP-8300 Series Epoxy Primer or AP-8030 Super-Fill Primer D.T.M. according to manufacturer's instructions. Allow sufficient flash times for solvents to escape film. Insufficient flash times will lead to retarded hardness development of the total system.

Basecoat

For best results, follow flash times and film thickness recommendations of the basecoat supplier. Note: flash times vary between basecoats and are dependent on the shop temperature and air movement. Insufficient basecoat flash time may lead to movement of the basecoat metallic pigments and loss of clearcoat gloss.

Mixing Directions

2 Parts AC-9041
1 Part AH-6370, AH-6380 or AH-6390

Euro-Gloss Clear
Urethane Catalyst

Once catalyzed, AC-9041 is ready to spray. However, for specific shop conditions, AC-9041 can be reduced or retarded with up to 10% AR series Universal Reducers or AR-2100 Retarder. In cold weather, the addition of AS-X99 Universal Urethane Cure Accelerator will speed cure. However, care should be exercised in the addition of cure accelerators to urethane products. A significant reduction in potlife and a loss of clearcoat gloss can occur if over catalyzed.

Application

Adjust air pressure at the gun to 45-50 psi for siphon feed guns or 6-10 psi when using a HVLP. Use less pressure to minimize over spray on small jobs. Apply 2-3 wet coats at a gun distance of 8-12 inches allowing each coat to become hand slick before applying the next coat. Recoat times will vary with temperature and air movement between 10 and 30 minutes. Apply each coat of clear within 30 minutes flash of the previous coat to prevent possible recoat lift. Recommended dry film thickness is 1.8 to 2.5 mils.

Blending Procedure

Before blending the panel with clear, the blended area must be washed and scuff sanded thoroughly with a good quality wax and grease remover such as AS-2900. Apply wet coats of clear to cover the repaired area and slightly beyond. Allow recommended flash times between coats. Extend the second coat 4 to 8 inches beyond the first coat. Begin application of the final coat 4 to 8 inches beyond the second coat and spray into the center of the painted area. Best results can be achieved by the addition of 10% to 50% of a urethane grade reducer in the last coat. Any dry edges remaining can be melted in immediately by misting with a second gun containing a medium temperature urethane reducer.

Drying Schedule

Dry times are based on recommended film thickness and are dependent on ambient temperature. Excessive film thicknesses, low temperature and poor air movement will retard dry times.

		<u>Air Dry</u>		
Dust Free	10-15 min	Buffable	8-12 hours	
Tack Free	20-30 min	To Deliver	8-12 hours	

Force Dry Times

Allow 10-15 minutes flash time of final coat of clear when using infrared or radiant heat.

		<u>Temperature</u>			
110°F	45 min	120°F	45 min	140°F	30 min

Buffing

If buffing is needed to remove dirt, allow the clearcoat to dry the recommended time then wet sand with 800-1000 grit sandpaper followed by 1500 grit sandpaper. When all 800-1000 scratches are removed, buff with a fine grade liquid rubbing compound followed by a polish or glaze compound applied by hand or machine. AH-390HS can be buffed for several days after application.

Technical Data

Weight Solids		Mixing Ratio	2:1
Package	47.0%	Air Pressure @ Gun	35-50 psi
Ready to spray 2/1	45.0%	Recommended Film Thickness	1.8 - 2.5 mil
Volume Solids		Flash Point	0°F TCC
Package	40.0%	Gloss	90+
Ready to spray 2/1	38.0%	DOI	Excellent
mil		Pot Life	6 to 10 hours
VOC @ Gun 2/1	4.2 lbs/gal	Coverage Ready to Spray 2/1	608 sq ft@1
		Viscosity @ Gun	16-19 #2Zahn

Performance Data

Flexibility	Excellent	Direct Impact	Excellent	Chip Resistance	Excellent
Salt Resistance	Excellent	Humidity Resistance	Excellent	Hardness	3H