



Tech Data Sheet

Universal Primer Zinc Chromate Primer

PRODUCTS CPS-26 Yellow Zinc Chromate																							
FEATURES																							
An excellent choice when the job calls for something better than an alkyd primer, but still dictates the economies of a single pack product. A much better and faster primer than an alkyd when used under urethanes, or any system with a high solvent strength. Very little chance of incurring any recoat lifting. Also, the Zinc Chromate component helps with adhesion to those problem metals: aluminum, galvanized, etc.																							
DESCRIPTION A rust-inhibitive primer for application to steel surfaces. It provides excellent protection, adhesion, wetting, and application properties.	RECOMMENDED USES May be used for interior or exterior surface under alkyd, oil, oleoresinous and latex top coats. For structural steel, tanks, piping, equipment, etc.																						
PHYSICAL PROPERTIES <table border="0"> <tr><td>GENERIC TYPE</td><td>Phenolic Modified Zinc Chromate</td></tr> <tr><td>COLOR</td><td>Yellow</td></tr> <tr><td>GLOSS</td><td>Flat</td></tr> <tr><td>SOLID CONTENT</td><td>62% by weight, 53% by volume</td></tr> <tr><td>VISCOSITY</td><td>68 +/- 2 KU</td></tr> <tr><td>SHELF LIFE</td><td>One year</td></tr> <tr><td>FLASH POINT</td><td>55°F</td></tr> <tr><td>MAX TEMP.</td><td>225°F Continuous 330°F Intermittent</td></tr> <tr><td>COVERAGE</td><td>802sq.ft. per gal. at 1mil (theoretical coverage)</td></tr> <tr><td>THICKNESS</td><td>Recommended 1.5-2.0mil DFT</td></tr> <tr><td>DRY TIMES</td><td>2 hours to tack free 5 hours to recoat 8 hours to dry hard</td></tr> </table>	GENERIC TYPE	Phenolic Modified Zinc Chromate	COLOR	Yellow	GLOSS	Flat	SOLID CONTENT	62% by weight, 53% by volume	VISCOSITY	68 +/- 2 KU	SHELF LIFE	One year	FLASH POINT	55°F	MAX TEMP.	225°F Continuous 330°F Intermittent	COVERAGE	802sq.ft. per gal. at 1mil (theoretical coverage)	THICKNESS	Recommended 1.5-2.0mil DFT	DRY TIMES	2 hours to tack free 5 hours to recoat 8 hours to dry hard	SURFACE PREPARATION All surfaces must be dry, clean, and free from all dirt, oil, and grease. Remove all loose or scaling paint. Clean any oil, grease or wax residue. For best results, abrasive blast SSPC-SP-6.
GENERIC TYPE	Phenolic Modified Zinc Chromate																						
COLOR	Yellow																						
GLOSS	Flat																						
SOLID CONTENT	62% by weight, 53% by volume																						
VISCOSITY	68 +/- 2 KU																						
SHELF LIFE	One year																						
FLASH POINT	55°F																						
MAX TEMP.	225°F Continuous 330°F Intermittent																						
COVERAGE	802sq.ft. per gal. at 1mil (theoretical coverage)																						
THICKNESS	Recommended 1.5-2.0mil DFT																						
DRY TIMES	2 hours to tack free 5 hours to recoat 8 hours to dry hard																						
	MIXING INSTRUCTIONS Mix well before using. Make sure to stir from bottom to top to ensure proper mixing. -1 Part Paint -10%-15% UR Series Reducer (spray application)																						
	EQUIPMENT The following equipment has been found suitable; however, equivalent equipment may be substituted. Air Spray: 1.6 -1.8 needle, Conventional or HVLP Airless: Graco 240-000 gun, 0.15 orifice, 30:1 pump																						
RECOATING For best results, application of additional coats should take place within 24 hours. Prolonged delays may require cleaning and roughening of the undercoat to ensure optimum intercoat adhesion.																							
APPLICATION																							
Do not apply in rain, excessive humidity or in freezing weather. For spray application, thin with UR Series Reducer or other appropriate thinner as needed. Thinning adds to VOC content - check local regulations. Apply paint over clean surfaces for best finish. Apply smooth even coats not to exceed 5 mils wet, as wrinkling (loss of gloss) and slowing of dry may occur from excessive one coat thickness. For additional information, contact authorized distributor. Brush, roller, or spray.																							
CLEAN UP																							
Clean all equipment immediately after use with UR Series Reducer or lacquer thinner.																							
CAUTIONS																							
CONTENTS ARE FLAMMABLE LIQUID Vapors may cause flash fires. Keep away from heat, sparks, and open flame. During use and until all vapors are gone. Keep area ventilated - Do not smoke - Extinguish all flames, pilot lights, and heaters - Turn off stoves, electric tools and appliances, and any other sources of ignition. VAPOR HARMFUL Use only with adequate ventilation. Wear an appropriate properly fitted vapor/particle respirator (NIOSH/OSHA approved) during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. FIRST AID: IF INHALED: If affected, remove from exposure. Restore breathing, keep warm and quiet. IF ON SKIN: Wash affected area thoroughly with soap and water. Remove contaminated clothing. Launder before re-use. IF IN EYES: Flush eyes with large amounts of water for 15 min. Get medical attention. IF SWALLOWED: Get medical attention immediately. SPILL AND WASTE: Remove all sources of ignition. Ventilate and remove with inert absorbent. Incinerate in approved facility. Do not incinerate closed container. Dispose of in accordance with Federal, State and Local regulation regarding pollution. DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE: Contains solvents which can cause permanent brain damage and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents can be harmful or fatal. DO NOT TAKE INTERNALLY - KEEP OUT OF REACH OF CHILDREN																							
WARRANTY																							
CPS Coatings guarantees the standard quality of this product and its adherence to our specifications. However, as the use of this product is beyond our control, we expressly disclaim responsibility for its handling, storage, use, results obtained or any injury or special indirect or consequential damage of any nature whatsoever.																							