



CPS COATINGS, INC. TECHNICAL DATA

CPS-4000 Series Polyurethane

Generic Type	Aliphatic Acrylic Urethane
Description	2 component high gloss polyurethane. Designed to be highly resistant to chemicals, salt water, UV lighting, and impact.
Color	All standard colors and others upon request
Solids Content	54% by volume and 59% by weight
Viscosity	60 - 65 +/- 2 KU (mixed)
Shelf Life	1 Year unmixed
Coverage Thickness	864 sq. ft. per gallon at 1 mil Recommended 1.5 - 2.0 mils DFT
Dry Time	15 min - Tack Free 45 min - 1 hour - Recoat
Solvent	UR-SERIES REDUCER
Recommended Uses	CPS-4000 series is recommended for storage tanks, transport trailers, sewage plants, offshore drilling platforms and equipment, air conditioning coils, pulp and paper industry, mine equipment, refineries and petrochemical plants.
Surface Preparation	Designed to be put over properly primed surfaces. For best results contact your CPS representative.
Application	Air Spray: DeVilbiss MBC gun, E needle, 704 air cap Airless: Graco 204-000 gun, 0.015 tip, 30:1 pump
Pot Life	8 Hours
Mix Ratio	3:1 with 898
Max Temperature	180 degrees F